

DAFTAR PUSTAKA

- [1].Arakawa H. et al. 2008. “ *Efficient Dyesensitized Solar Cells Using Zinc Oxide Powder*” National Inst. Materials and Chemical Res. July 2008.
- [2].Dally, James W et al. 2007. “*Using Less Explosive Eosine – Y and Mercurochrome* “. IEEE Trans. On PWRD. Vol. 2, p.205. 2007.
- [3].Elandbird, F et al. 2008. “ *Current-Voltage Characteristics of The Solar Cells With These Electrodes Were Examined*”. IEEE Transaction on Industry Applications, Vol. 7. No. 2. Jun. 2008. p 453 – 458.
- [4].Hara, Kojiro et al. 2007. “ *Oxide Semiconductor Thin Film Photoelectrode*” National Inst. Materials and Chemical Res. July 2007.
- [5]. Horiguchi, Toshiro et al. 2007. “*Dyesensitized Solar Cell (Graetzel cell) Uses a Titania Photo Electrode*”.Sumitomoosakasemento Shinkigiken.July 2007.
- [6].Janu, Kapoor et al. 2008 “ *Mercurochrome Dye Exhibits High Photoelectric Conversion Efficiency Over 60% in a Wide Region Up to 450-520nm*”. IEEE Trans.on PWRD. Vol. 2. No. 2. p.178. 2008
- [7].Kinoshita, Nobu et al. 2009. “*Solar Cell Performance Was Examined Usingthe Photo Electrodes of TiO₂*” Sumitomoosakasemento Shinkigiken. July 2009.